

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 2000-310859

(43)Date of publication of application : 07.11.2000

(51)Int.Cl.

G03F 7/039

G08F 8/00

H01L 21/027

(21)Application number : 2000-091921

(71)Applicant : TOKYO OHKA KOGYO CO LTD

(22)Date of filing : 30.10.1995


(72)Inventor : SATO KAZUFUMI
NITTA KAZUYUKI
YAMAZAKI AKIYOSHI
SAKAI TOMOAKI
NAKAYAMA TOSHIMASA

(54) BASE RESIN FOR POSITIVE RESIST

(57)Abstract:

PROBLEM TO BE SOLVED: To obtain a base resin for a positive resist having high sensitivity and high resolution, excellent in focal depth-width characteristics, shape secular change stability after exposure and the shelf stability of a resist solution and capable of forming a resist pattern excellent in profile shape by using a polyhydroxystyrene having a specified weight average molecular weight and a specified molecular weight distribution.

SOLUTION: The base resin for a positive resist comprises a polyhydroxystyrene having residues of the formula substituted for 10-60 mol% of hydroxyl groups and having a weight average molecular weight of 8,000-25,000 and a molecular weight distribution (Mw/Mn) of ≤ 1.5 . In the formula, R1 is H or methyl, R2 is methyl or ethyl and R3 is 1-4C lower alkyl. In the case of <10 mol% substitution rate, a pattern excellent in shape is not obtained. In the case of >60 mol%, the sensitivity of the resist lowers. The substituents are preferably 1-ethoxyethoxy and 1-methoxy-n-propoxy groups because these groups enhance sensitivity and resolving power in a well-balanced state.



LEGAL STATUS

[Date of request for examination] 30.03.2000

[Date of sending the examiner's decision of rejection] 06.03.2001

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]	3226270
[Date of registration]	31.08.2001
[Number of appeal against examiner's decision of rejection]	2001-05055
[Date of requesting appeal against examiner's decision of rejection]	04.04.2001
[Date of extinction of right]	

Copyright (C); 1998,2003 Japan Patent Office